



POLYKEN®

937 Brush Applied Mastic

Polyken® Pipeline Coatings

System Description

The Polyken 937 mastic is a cold applied coating designed to protect underground piping such as valves, T's, ells and couplings. Once applied, the Polyken mastic form a tough monolithic coating which resists cracking, crazing, or checking.

Product Advantages

- High solids
Conforms to Irregular Shapes
- Resists cracking, crazing, and checking
Reliable sleeve-type coating
- Easy Field Application
Established In-ground History
- Saves training costs and time references
Proven reliability with global

System Properties

	#937 Brush
Color	Black
Solvent	Toluene
Base	Polymeric Asphalt
Flash Point	3,33°C (38°F)
Specific Gravity	1.14
Solids %	69.5
Viscosity (Brookfield)	20,000 cps (#6,20)
Shelf Life	1 year

Coverage

Coverage rate is 1.85-1.95 sqm/l (75-80 sqft/gal) which will provide a dry film thickness of approximately 0.3 mm (12 mils).

Application temperature: 0°C (32°F) to 49°C (120°F)

Service temperature: -18°C (0°F) to 121°C (250°F)

Dry Time:	0.3 mm (12 mils) at 21°C (70°F)	To Touch	20 minutes
		To Backfill	2 hours

Ordering Information

937 B MASTIC 1 GAL (R28 BRUSH): 1 GAL or 3.78 L



CORROSION PROTECTION GROUP
www.berrycpg.com

The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics' written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics' liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

Local Distributor / Representative:

For contact details of local Distributors / Representatives
Please visit www.berrycpg.com.

Headquarters
Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berryplastics.com

Houston, TX, USA
Tel: +1 713 676 0085
US Toll Free: +1 888 676 7202
Fax: +1 713 676 0086
CPGH@berryplastics.com

Tijuana, Mexico
Tel USA +1 858 633 9797
Fax US: +1 858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 607 9105
CPGTJ@berryplastics.com

Westerlo, Belgium
Tel: +32 14 722500
Fax: +32 14 722570
CPGE@berryplastics.com

Baroda, India
Tel: +91 2667 264721
Fax: +91 2667 264724
CPGIN@berryplastics.com