



POLYKEN® 942CX & 955CX 3-Ply Co-extruded Coating System for New Pipelines and Existing Pipeline Rehabilitation

System Description

The Polyken 942/955CX System is a co-extruded multilayer coating system designed for the corrosion protection of pipelines operating in highly corrosive environments and exposed to high mechanical stresses that may be present particularly on large diameter pipes and is fully certified to the DIN EN 12068 Standard (Class C50). The system consists of #1027 liquid adhesive, #942CX three ply anti-corrosion inner layer and #955CX mechanical outer layer. The three ply adhesive system produces a strong cohesive bond to the primed steel surface, at the spiral overlap and to the mechanical outer layer. The tough mechanical properties of the outer layer provide protection to the pipes during handling and installation. For the coating of joints with other mainline coatings the Polyken 942/955EN system is preferred due to its better conformability.

Product Features/Benefits

- Fully amalgamating overlapping areas
Forming a sleeve-type coating
- Worldwide reference lists
Proven long-term in-ground performance
- Impermeable to oxygen and moisture
- Resistant to soil stress
Superior in-ground performance
- Uniform coating thickness
Plant coating quality with in-situ application
- Low cathodic protection-current requirements
Saving cost over the life of the pipeline
- Co-extruded Polyethylene and Butyl Rubber
Superior cohesive strength

Product Selection Guide

Max operating temperature	65°C (150°F)
Recommended primer	1027
Recommended pipe preparation	ST2 1/2 - ST3 or SA 2 1/2
Compatible line coatings	PE, FBE, CTE, Tape and Coal Tar
Total installed tape system thickness	min 2.5 mm (100 mils)
Performance	DIN EN 12068; Class C50

Product Properties	Test method	Typical Value	
		942-20CX	955-30CX
Tensile Strength	EN12068	>25 pli (4.4 N/mm)	> 45pli (7.9 N/mm)
Elongation	EN12068	> 300%	> 300%
Saponification value	DIN30672	< 1	< 1

System Properties Two layers 942-20CX and two layers 955-30CX

	Test method	Requirement	Typical Value
Shear Resistance to Primed Steel	EN12068	> 0.05 N/mm ²	0.08 N/mm ²
Peel Adhesion to Primed Steel	EN12068	> 1.0 N/mm (5.7 pli)	1.2 N/mm (6.9 pli)
Peel Adhesion Inner to Inner	EN12068	> 1.5 N/mm (8.5 pli)	2.8 N/mm (15.9 pli)
Peel Adhesion Outer to Inner	EN12068	> 1.5 N/mm (8.5 pli)	3.0 N/mm (17.0 pli)
Peel Adhesion Outer to Outer	EN12068	> 0.2 N/mm (1.1 pli)	0.7 N/mm (4.0 pli)
Cathodic Disbondment:	EN12068	< 20 mm radius	< 5 mm radius
Specific Electrical Resistance	EN12068	> 10 ⁸ ohm•m ²	2 X 10 ¹¹ ohm•m ²
Dielectric Strength	ASTM D149		50 kV
Impact resistance	EN12068, class C50	> 15 J	>15 J
Penetration resistance	EN12068, class C50	> 0.6 mm remaining thickness	1.6 mm remaining thickness

Ordering Information

Polyken 942CX and 955CX Tape Coatings are available in roll form

Example : **942CX 4X50FT 4.1CM**

942CX	Product type	Standard Ordering options
4	Tape width in inches	2" (50 mm), 4" (101 mm), 6" (152 mm)
50	Tape roll length in feet	50 ft (15.2M), 100 ft (30.5 M), 200 ft (61 M), 400 ft (122 M)
4.1CM	Core inside diameter	3" or 76 mm, 1.6" or 41 mm

Example : **955CX 4X50FT 4.1CM**

955CX	Product type	Standard Ordering options
BLK	Tape backing color	White (WHT), Black (BLK)
4	Tape width in inches	2" (50 mm), 4" (101 mm), 6" (152 mm)
50	Tape roll length in feet	50 ft (15.2M), 100 ft (30.5 M), 200 ft (61 M)
4.1CM	Core inside diameter	3" or 76 mm, 1.6" or 41 mm

Note : 942/955CX tapes are installed with 1027 liquid adhesive, see latest datasheet for 1027, DS-1027

For other ordering options please contact your Berry Plastics representative.

Equation for Pipe Coating Requirements

$$\frac{(\text{Width of Coating in inches}) \times (\text{Area of pipe in square feet})^*}{(\text{Width of Coating in inches} - \text{Overlap in inches}) \times 100} = \text{Squares}^{**} \text{ of Coating Required}$$

* Area of pipe in square feet = (Diameter in inches) / 12 x 3.1416 x (Length in ft)

** One Square = One hundred square feet = 9.29 square meters

$$\frac{(\text{Width of Coating in mm}) \times (\text{Area of pipe in square meter})^*}{(\text{Width of Coating in mm} - \text{Overlap in mm})} = \text{Square meters of Coating Required}$$

*Area of pipe in square meter = (Diameter in mm) /1000 x 3.1416 x (Length in meter)

DS-942-955-CX-REV3-Jan12 AARPS-0156



The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

Local Distributor / Representative:

For contact details of local Distributors / Representatives
Please visit www.berrycpg.com.

Headquarters
Franklin, MA, USA
Tel: +1 508 918 1714
US Toll Free: +1 800 248 0149
Fax: +1 508 918 1910
CPG@berrypastics.com

Houston, TX, USA
Tel: +1 713 676 0085
US Toll Free: +1 888 676 7202
Fax: +1 713 676 0086
CPGH@berrypastics.com

Tijuana, Mexico
Tel USA +1 858 633 9797
Fax US: +1 858 633 9740
Tel Mexico: +52 664 647 4397
Fax Mexico: +52 664 607 9105
CPGTJ@berrypastics.com

Westerlo, Belgium
Tel. +32 14 722500
Fax +32 14 722570
CPGE@berrypastics.com

Baroda, India
Tel: +91 2667 264721
Fax: +91 2667 264724
CPGIN@berrypastics.com