

DS-S1080-REV1-FEB11 - LEXPS0084

Characteristics: S1080 is a hotmelt based adhesive delivered on rolls.

Applications: S1080 is used in combination with heat shrinkable casings for pre-

insulated pipes. Maximum operating temperature is 65°C.

Product description: S1080-XXXxYYYxZZZZ

> XXX = Width in mm YYY = Thickness in mm ZZZ =Length in mm

Material properties:

Property	Test Method	Condition	Requirement	Typical value
Softening point	ASTM E28		90°C minimum	103°C
Low temperature flexibility	ASTM D2671	Method C bending on Ø 100 mm	Below -25°C	- 40°C
Shear strength	EN12068	23°C	0.05 N/mm ² minimum	2.6 N/mm ²

Standard Dimensions: Width = 50 mm

> Thickness = 1 mm Length = 30000 mm

Product printing: No printing

Product labeling: The box containing S1080 rolls is labeled with Covalence logo,

Product description, Quantity and Lot number.



The leading global partner in protecting the integrity of critical infrastructure.

Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the right.

Local Distributor / Representative:

For contact details of local Distributors / Representatives Please visit www.berrycpg.com.

www.berrycpg.com Headquarters

Franklin, MA, USA Tel: +1 508 918 1714 US Toll Free: +1 800 248 0149 Fax: +1 508 918 1910 CPG@berryplastics.com

Houston, TX, USA Tel: +1 713 676 0085 US Toll Free: +1 888 676 7202 Fax:+1 713 676 0086 CPGH@berryplastics.com

Tijuana, Mexico Tel USA +1 858 633 9797 Fax US: +1 858 633 9740 Tel Mexico: +52 664 647 4397 Fax Mexico: +52 664 607 9105

CPGTJ@berryplastics.com

Westerlo, Belgium Tel. +32 14 722500 Fax +32 14 722570 CPGE@berryplastics.com Baroda, India Tel: +91 2667 264721 Fax: +91 2667 264724 CPGIN@berryplastics.com