

COVALENCE[®] HTLP60-HP

Product Information

A girth weld protection system for three-layer coated pipes.

Product description: Covalence[®] HTLP60-HP system is a wrap-around heat-shrinkable sleeve which replicates the structure and performance of mill-applied three-layer PE coatings. HTLP60-HP also has excellent compatibility and has been extensively used on many other mill-applied coatings (see below).

- **Market:** Oil and gas pipelines.
- **Application:** Bends, elbow, fittings and T's, girth weld, pipeline rehabilitation, field applied (ODT).

Construction: Three-layer system

- **First layer:** Liquid epoxy, solvent-free two-component.
- **Second layer:** High shear strength copolymer adhesive.
- **Third layer:** Radiation cross-linked, high density polyethylene with permanent Change Indicator (PCI).

During installation, the epoxy is applied to the prepared pipe surface and the heat-shrinkable sleeve is immediately wrapped around the joint over the wet epoxy. Heat is then applied to the sleeve which shrinks to form a tight fit around the joint. While curing, the epoxy forms strong mechanical and chemical bonds to the pipe surface & to the copolymer adhesive layer. The radiation cross-linked outer layer forms a tough barrier against mechanical damage and moisture transmission.

Features:

- Fully resistant to shear forces induced by soil and thermal movements.
- Sleeve applied over wet epoxy, allowing formation of strong mechanical & chemical bonds.
- Superior cathodic disbondment and hot water immersion resistance.
- Fully reconstructs the coating of three-layer coated pipes.
- Dimpled backing provides a "permanent change" indicator for application of heat.

Benefits:

- The HTLP is tough & lasts as long as a 3-layer, mill-applied coating.
- Allows fast application combined with high performance!
- Offers the optimum barrier protection against corrosion.
- HTLP systems allow the pipeline to have a virtually monolithic coating system.
- Ensures correct application heat & allows easy post-heat inspection. Reliable inspectability at any time.

Product selection guide

Max operating temperature	65°C (149°F).
Compatible line coatings	PE, FBE, Coal Tar, DFBE
Min. preheat temperature	70°C (158°F)
Recommended pipe preparation	Sa 2½
Soil stress restrictions	None
Performance	EN 12068 Class C60 UV

Product properties Covalence[®] HTLP60-HP

Backing

Property	Test method	Typical value
Tensile strength at break	ASTM D 638	3300 psi (22.8 MPa)
Elongation at break	ASTM D 638	600%
Hardness, Shore D	ASTM D 2240	57
Shrink force	ASTM D 638, 150°C (302°F)	40 psi
Dielectric strength	ASTM D 149	900 V/mil (35 kV/mm)
Moisture absorption	ASTM D 570	0.04%

Adhesive

Property	Test method	Typical value
Softening point	ASTM E 28	107°C (225°F)
Lap shear	EN 12068 @ 10 mm (0.4")/min	0.22 N/mm ² @ 60°C (140°F)

Installed sleeve

Property	Test method	Typical value
Peel to steel	EN 12068 @ 10 mm (0.4")/min	7 N/mm
Cathodic disbondment	EN 12068 28 days, @ 60°C (140°F)	5 mm radius
Hot water immersion	ASTM D 870 120 days, @ 60°C (140°F)	No delamination, no blisters or water ingress
Soil stress creep resistance	TP-206 65°C (149°F)	0.003 mm (0.0001 in)
Low temperature flexibility	ASTM D 2671-C	-40°C (-40°F)
Impact resistance	EN 12068, Class C	> 15 J *
Indentation resistance	EN 12068, Class C @ 60°C (140°F)	Residual thickness > 0.6 mm *

* Construction /1.0-1.5 or thicker.

Product thickness

Designation /...	/B	/1-1.5*	/1.2-1.5*	/C
Backing as supplied	0.75 mm (0.030 in)	0.75 mm (0.030 in)	0.90 mm (0.035 in)	1.04 mm (0.041 in)
Backing fully free recovered	1.00 mm (0.039 in)	1.00 mm (0.039 in)	1.20 mm (0.047 in)	1.40 mm (0.055 in)
Adhesive as supplied	1.00 mm (0.039 in)	1.50 mm (0.060 in)	1.50 mm (0.060 in)	1.50 mm (0.060 in)

* Minimum order quantities apply

General order information		General order information (continued)	
<p>Covalence® HTLP type products are available</p> <ul style="list-style-type: none"> - As cut piece (pre-cut with separate closure patch) - As Uni-sleeve (pre-cut with attached closure patch) - As a roll (closure patches to be ordered separately) <p>Select sleeve width that will overlap onto the mill-applied coating by 50 mm (2 inches) minimum on each side of the weld joint. Take a 10% shrinkage during installation of sleeve into account when calculating minimum sleeve width.</p>		<p>Recommended primer HTP60-HP type products are installed with S1301-M epoxy primer . Epoxy primers are ordered separately. For more ordering information on epoxy primers see application tables DS-S1301M. As field application of primers may vary, consult a Seal For Life Representative or Authorized Distributor for rate of coverage guidance.</p> <p>Handling Handle with care. Keep boxes upright.</p> <p>Storage Store indoor, clean and dry, away from direct sunlight in a cool place below +50°C. Unlimited shelf life.</p>	
Cut piece / Uni-sleeve		Information	
Example	HTLP60-HP-16000X17/B/(UNI)	Documentation	Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our head office, from our local distributor or by sending an email to info@sealforlife.com
	Designation	Standard ordering options	
60	Operating temperature (°C)	60 (=65°C (149°F))	
16000	Outside pipe diameter (mils)	2.375 – 100.000 (DN50 – DN2500)	
17	Sleeve width (in) (Sw)	17 (17.75 or 450 mm)* 20 (20.25 or 514 mm)* 24 (23.50 or 600 mm)*	
/B	Product thickness	/B /1.0-1.5 /1.2-1.0	
UNI	Designates pre-attached closure patch	Optional	
		* nominal width	
Roll form (closure patch to be ordered separately)		Certified staff	Application of the described coating system should be carried out by certified personnel.
Example	HTLP60-HP-20X100/1-1.5-RL		
	Designation	Standard ordering options	
60	Operating temperature (°C)	60 (=65°C (149°F))	
20	Roll width (in) (Sw)	17 (17.75" or 450 mm)* 20 (20.25" or 514 mm)* 24 (23.50" or 600 mm)*	
100	Roll length (ft) (Sl)	100 ft (= 30 m)	
/1-1.5	Product thickness	/B /1.0-1.5 /1.2-1.0	
		* nominal width	
Closure patches (to be ordered separately)			
Example	WPCP-IV-4X17		
	Designation	Standard ordering options	
4	Patch width (in) (Pw)	4 (100 mm) 6 (150 mm) 8 (200 mm)	
17	Patch length (in) (Pl)	17 (17.75" or 450 mm)* 20 (20.25" or 514 mm)* 24 (23.50" or 600 mm)*	
		* nominal width	

Sleeve cut lengths and appropriate closure patch widths depend on the pipe size and product construction, see latest application AT-GIRTHWELD.

For proper product installation, see latest installation instruction.

 <p>SEALFORLIFE Industries</p> <p><small>PART OF THE BERRY PLASTICS ENGINEERED MATERIALS DIVISION</small></p>	<p>Seal For Life Industries LLC Franklin, MA, USA Tel: +1 508 918 1600 Toll Free: +1 800 248 7659 Fax: +1 508 918 1905 franklin@sealforlife.com</p>	<p>Seal For Life Industries Tijuana, Mexico Tel USA: +1 858 633 9797 Fax USA: +1 858 633 9740 Tel Mx: +52 664 647 4397 Fax Mx: +52 664 607 9105 mexico@sealforlife.com</p>	<p>Seal For Life Industries Stopaq B.V. Stadskanaal, the Netherlands Tel: +31 599 696 170 Fax: +31 599 696 177 info@sealforlife.com</p>	<p>Seal For Life Industries BVBA Westerlo, Belgium Tel: +32 14 722 500 Tel: +32 14 722 570 Fax: +32 14 722 570 belgium@sealforlife.com</p>	<p>Seal For Life India Private Ltd. Baroda, India Tel: +91 2667 264 721 Tel: +91 2667 264 724 Fax: +91 2667 264 724 india@sealforlife.com</p>
	<p>Anodefex® - Stopaq® - Polyken® - Covalence® - Powercrete® - Sealtaq® - Blockr® - Elasto.Qote®</p>				

DISCLAIMER: Seal For Life Industries warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Seal For Life Industries written instructions. Since many installation factors are beyond the control of Seal For Life Industries, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Seal For Life Industries liability is stated in the standard terms and conditions of sale. Seal For Life Industries makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date on the left. Covalence® is a registered trademark of Seal For Life Industries.