

POLYKEN[®] YGIII

Product Information

Product description: The Polyken[®] YGIII System is a multilayer coating system used primarily for the protection of steel and ductile iron water pipelines. Polyken[®] 1019, low VOC Polyken[®] 1033A and Zero VOC Polyken[®] 1039 liquid adhesives provide a uniformly smooth contact surface to promote high adhesion of the coating system to the pipe. Liquid Adhesives are formulated with corrosion inhibitors and adhesion promoters. The unique formulation flows and fills surface profiles and irregularities. The Anti-Corrosion layer Polyken[®] 989 is engineered to assure a high bond to the primed surface with excellent conformability characteristics. The Middle and Outer mechanical protection layers Polyken[®] 955 and 956 achieve a complete bond to the 989 inner layer, providing maximum handling and in-service protection for the coating system. The adhesives in these and all Polyken[®] tape systems contain proven anti-microbial additives.

Features:

- Worldwide reference lists.
- Impermeable to oxygen and moisture.
- Resistant to soil stress.
- Zero VOC coating system available.
- Uniform coating thickness.
- Low cathodic protection-current requirements.
- Exceeds AWWA standards.
- Compatible with large pipe diameters.

Benefits:

- Proven long-term performance.
- Low cathodic protection costs. Saving cost over the life of the pipeline.
- Superior in-ground performance.
- Environmentally friendly.
- Easy to apply.
- Saving cost over the life of the pipeline.
- Reliable, high performance corrosion protection.
- Minimizes inventory, thus saving money.

Product selection guide

Max. operating temperature	85°C (185°F)
Recommended primer	1019, 1033A or 1039
Recommended pipe preparation	SSPC-SP6 /NACE3 or SA 2 ½
Performance	AWWA C-214

Product construction

	Inner Layer 989-20	Middle Layer 955-30	Outer Layer 952/956-30
Backing	9 mils (0.229 mm)	25 mils (0.635 mm)	25 mils (0.635 mm)
Adhesive	11 mils (0.279 mm)	5 mils (0.127 mm)	5 mils (0.127 mm)
Backing color	Black	Gray	White, Blue

Ordering information

Polyken [®] 989, 955 and 956 Tape Coatings are available in roll form.		
Example	989-20 BLK 12X1000	
989	Product type	Standard Ordering options
20	Total tape thickness in mils	20 mils (0.51 mm)
BLK	Tape backing color	Black (BLK)
12	Tape width in inches	4" (101mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
	955-30 GRA 12X1000	
955	Product type	Standard Ordering options
30	Total tape thickness in mils	30 mils (0.762 mm)
GRA	Tape backing color	Gray (GRA)
12	Tape width in inches	4" (101 mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
	952/956-30 WHI UVI 12X1000	
956	Product type	Standard Ordering options
30	Total tape thickness in mils	30 mils (0.762 mm)
WHI	Tape backing color	White (WHI), Blue (BLU)
12	Tape width in inches	4" (101 mm), 6" (152 mm), 9" (228 mm), 12" (305 mm), 18" (457 mm)
1000	Tape roll length in feet	800 ft (244 m), 1000 ft (305 m)
UVI	Designates Ultraviolet Protection	Standard

For other ordering options please contact your Seal For Life representative.

DISCLAIMER: Berry Plastics warrants that the product(s) represented within conform(s) to its/their chemical and physical description and is appropriate for the use as stated on the respective technical data sheet when used in compliance with Berry Plastics written instructions. Since many installation factors are beyond the control of Berry Plastics, the user is obligated to determine the suitability of the products for the intended use and assume all risks and liabilities in connection herewith. Berry Plastics liability is stated in the standard terms and conditions of sale. Berry Plastics makes no other warranty either expressed or implied. All information contained in the respective technical data sheet(s) should be used as a guide and is subject to change without notice. This document supersedes all previous revisions. Please see revision date below. Polyken[®] is a registered trademark of Berry Plastics Corporation.

Product properties of Polyken[®] YGIII

Property	Method	Typical values		Units
		989-20	955-30 & 956-30	
Tensile strength	ASTM D1000	30 5.3	50-65 8.8-11.4	pli N/mm
Elongation	ASTM D1000	300	300-400	%
System properties 80 mils system: 989-20 + 955-30 + 956-30				
Peel adhesion to primed steel	ASTM D1000	18.7 3.3		pli N/mm
Cathodic disbondment	ASTM G8	0.25 6.4		in radius mm radius
Water vapor transmission	ASTM E96B	0.07		perm
Water vapor transmission rate	ASTM F1249 (100°F, 100%RH)	0.03 0.5		g/100in ² /24 hr g/m ² /24hr
Volume resistivity	ASTM E257	10 ¹⁵		Ω.cm
Dielectric breakdown	ASTM D1000	650 25.6		V/mil kV/mm
Dielectric strength	ASTM D149	20-23		kV
Impact resistance	ASTM G-14	90 10		in-lb J
Impact resistance	ASTM G-13	1000 4450		lb N
Penetration resistance	ASTM G-17	11-15		%

Equation for Pipe Coating Requirements

Squares of coating required** = $\frac{(\text{width of coating in inches}) \times (\text{area of pipe in square feet})}{(\text{width of coating in inches} - \text{overlap in inches}) \times 100}$

* Area of pipe in ft² = (diameter in inches / 12) x 3.1416 x length in feet
 ** One Square = one hundred square feet = 9.29 square meters

Square meters of coating required = $\frac{(\text{width of coating in mm}) \times (\text{area of pipe in square meter})}{(\text{width of coating in mm} - \text{overlap in mm}) \times 100}$

* Area of pipe in m² = (diameter in mm / 1000) x 3.1416 x length in meter

Information

Documentation	Extensive information is available on our web-site. Application instructions and other documentation can be obtained by contacting our offices, from our local distributor or by sending an email to info@sealforlife.com
Certified staff	Application of the described coating system should be carried out by certified personnel.



PART OF THE BERRY PLASTICS ENGINEERED MATERIALS DIVISION
 Anodeflox[®] – Stopaq[®] – Polyken[®] – Covalence[®] – Powercrete[®]

SEAL FOR LIFE TECHNOLOGY CENTRE
 Gasselterstraat 20, 9503 JB Stadskanaal
 the Netherlands
www.sealforlife.com

Seal For Life Industries LLC
 Houston, TX, USA
 Tel: +1 713 676 0085
 US Toll Free: +1 888 676 7202
 Fax: +1 713 676 0086
houston@sealforlife.com

Seal For Life Industries BV
 Stadskanaal, the Netherlands
 Tel: +31 599 696 170
 Fax: +31 599 696 177
info@sealforlife.com

Seal For Life Industries
 Tijuana, Mexico
 Tel USA: +1 858 633 9797
 Fax USA: +1 858 633 9740
 Tel Mexico: +52 664 647 4397
 Fax Mexico: +52 664 607 9105
mexico@sealforlife.com

Seal For Life Industries BVBA
 Westerlo, Belgium
 Tel: +32 14 722 500
 Fax: +32 14 722 570
belgium@sealforlife.com

Seal For Life Private Ltd.
 Baroda, India
 Tel: +91 2667 264 721
 Fax: +91 2667 264 724
india@sealforlife.com